

# PRODUCT DATA SHEET

## SikaCor® EG-5

2-pack AY-PUR top coat

Made in Germany

### DESCRIPTION

SikaCor® EG-5 is a 2-pack acrylic polyurethane top coat.

By adding 1 % b.w. SikaCor® PUR Accelerator (see product data sheet for more information) a fast touch and through drying will be achieved.

### USES

SikaCor® EG-5 may only be used by experienced professionals.

In combination with 2-pack primer and intermediate coats of the SikaCor® and Sika® Permacor® product range for heavy duty corrosion protection of atmospheric exposed and submerged steel structures. SikaCor® EG-5 can also be used as a line marking paint on selflevelling and broadcasted epoxy and polyurethane resin based floors e. g. for car parks.

### CHARACTERISTICS / ADVANTAGES

- Very good corrosion protection properties
- Tough elastic and hard but not brittle
- Largely insensitive against shock and impact
- Excellent chemical, weather and colour stability

### APPROVALS / CERTIFICATES

- Approved according to German standard 'TL/TP-KOR-Stahlbauten, Blatt 87 and Blatt 94'.
- In combination with SikaCor® PUR Accelerator, SikaCor® EG-5 is approved according to German standard 'TL/TP-KOR-Stahlbauten, Blatt 97'.
- Approved according to Austrian standard RVS 15.05.11 and RVS 08.09.02 Systems S11, S13, S14, S15, S16, S17, S18, S19 and S21.

### PRODUCT INFORMATION

<b>Packaging</b>	SikaCor® EG-5	30 kg and 10 kg net.
	Sika® Thinner EG	25 l, 10 l and 3 l
	SikaCor® Cleaner	160 l and 25 l
<b>Appearance and colour</b>	RAL and NCS colour shades	
<b>Shelf life</b>	2 years	
<b>Storage conditions</b>	In originally sealed containers in a cool and dry environment.	
<b>Density</b>	~1.3 kg/l	
<b>Solid content</b>	~61 % by volume	
	~74 % by weight	

#### PRODUCT DATA SHEET

SikaCor® EG-5

February 2022, Version 08.02

020602000040000004

## TECHNICAL INFORMATION

<b>Chemical resistance</b>	Weather, water, sewage, seawater, smoke, de-icing salts, acid and lye vapours, oils, grease and short term exposure to fuels and solvents.
<b>Temperature resistance</b>	Dry heat up to + 150°C, short term up to + 200°C Damp heat up to approx. + 50°C In case of higher temperatures please consult Sika. An exposure to high temperatures can lead to color changes.

## SYSTEM INFORMATION

<b>System</b>	<b>Steel:</b> Used as top coat on 2-pack primer and intermediate coats of the SikaCor® and Sika® Permacor® product range.  <b>Hot dip galvanized steel, stainless steel and aluminium:</b> 1 x SikaCor® EG-1 / EG-1 Plus / EG-1 VHS 1 x SikaCor® EG-5  <b>Selflevelling and broadcasted floors:</b> 1x SikaCor® EG-5  In case of light colours a second top coat of SikaCor® EG-5 may become necessary to achieve perfect opacity.
---------------	--

## APPLICATION INFORMATION

<b>Mixing ratio</b>	Components A : B	
	By weight	90 : 10
	By volume	7.1 : 1*
	*The volumetric mixing ratio may vary depending on the colour shade. Please refer to us, if needed.	
<b>Thinner</b>	Sika® Thinner EG If necessary max. 5% Sika® Thinner EG may be added to adapt the viscosity.	
<b>Consumption</b>	Theoretical material-consumption/VOC without loss for medium dry film thickness:	
	Dry film thickness	60 µm                      80 µm
	Wet film thickness	100 µm                      130 µm
	Consumption	~0.130 kg/m <sup>2</sup> ~0.170 kg/m <sup>2</sup>
	VOC	~33 g/m <sup>2</sup> ~44 g/m <sup>2</sup>
	If used as line marking paint on floors the consumption is approx. 0.20 kg/m <sup>2</sup> .	
<b>Material temperature</b>	Min. + 5°C	
<b>Relative air humidity</b>	Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point. The surface must be dry and free from ice.	
<b>Surface temperature</b>	Min. + 5°C 0°C by adding SikaCor® PUR Accelerator	
<b>Pot Life</b>	At + 10°C	~7 h                      ~5 h *
	At + 20°C	~5 h                      ~3 h *
	At + 30°C	~4 h                      ~2 h *
	* By adding 1 % b.w. SikaCor® PUR Accelerator	

## Drying stage 6

	Dry film thickness 80 µm	(ISO 9117-5)
+ 5°C after	21 h	
+ 10°C after	18 h	
+ 20°C after	14 h	
+ 40°C after	3 h	
+ 80°C after	45 min	
By adding 1 % b.w. SikaCor® PUR Accelerator:		
	Dry film thickness 80 µm	(ISO 9117-5)
0°C after	52 h	
+ 5°C after	18 h	
+ 10°C after	13 h	
+ 20°C after	5 h	

<b>Waiting time to overcoating</b>	Min. until drying stage 6 is achieved Max. unlimited Prior to further applications possible contamination must be removed.
------------------------------------	--

<b>Drying time</b>	<b>Final drying time</b> Depending on film thickness and temperature full hardness is achieved after 1 - 2 weeks. Tests of the completed coating system should only be carried out after final curing.
--------------------	---

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

#### Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944-4. Free from dirt, oil and grease.

#### Hot dip galv. steel, stainless steel and aluminium:

Free from dirt, oil, grease and corrosion products. In case of permanent immersion and condensation the surfaces must be slightly sweep blasted with non-ferrous abrasives.

For contaminated surfaces e.g. galvanized or primed areas we recommend to clean with SikaCor® Wash.

#### Selflevelling and broadcasted floors:

Free from dirt, oil, grease and dust. The surfaces must be slightly roughened e. g. by grinding.

### MIXING

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approx. 300

rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

### APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

#### By brush and roller

#### Conventional high pressure spraying:

- Nozzle size 1.5 - 2.5 mm
- Pressure 3 - 5 bar
- Oil and water trap is compulsory

#### Airless-spraying:

- Pressure min. 180 bar
- Nozzle size 0.38 - 0.53 mm (0.015 - 0.021 inch)
- Spraying angle 40° - 80°

### CLEANING OF EQUIPMENT

SikaCor® Cleaner

Spraying equipment must be rinsed with Sika® Thinner EG before using SikaCor® EG-5.

#### PRODUCT DATA SHEET

SikaCor® EG-5

February 2022, Version 08.02  
020602000040000004

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Deutschland GmbH

Industrial Coatings  
Rieter Tal  
D-71665 Vaihingen / Enz  
Phone: +49 (0)7042 109-0  
industrial-coatings@de.sika.com  
www.sika.de



### PRODUCT DATA SHEET

SikaCor® EG-5  
February 2022, Version 08.02  
020602000040000004

SikaCorEG-5-en-DE-(02-2022)-8-2.pdf