

PRODUCT DATA SHEET

Sika® ViscoCrete®-125 P

High-Performance Superplasticizer



DESCRIPTION

Sika® ViscoCrete®-125 P is a high-performance, superplasticizer and water reducer in powder form, based on Sika® ViscoCrete® polycarboxylate (PCE) polymer technology.

USES

Sika® ViscoCrete®-125 P is formulated for use in dry mortar applications and can be used with different hydraulic binder systems according to the performance required, including:

- Portland cement (OPC) and cement blends
- Ternary blended binders
- Calcium sulphate (gypsum) based binders

Sika® ViscoCrete®-125 P is especially suitable for the following dry-mortar applications:

- Cement and anhydrite screeds (including self-leveling screeds) and underlayments
- Grouts (including non-shrink grouts) & tile adhesives based on Portland cement (OPC).

CHARACTERISTICS / ADVANTAGES

Sika® ViscoCrete® is adsorbed onto the surface of the binder particles and due to repulsive forces from the effect known as steric hindrance, the solid binder particles are very effectively dispersed in the mix. The characteristics and advantages of Sika® ViscoCrete®-125 P include:

- High water reduction at low dosage (resulting in shorter drying times, higher densities and strengths)
- Very good flow and self-levelling behaviour
- Reduced mixing times due to fast adsorption
- Long-term stability which enables long slump life
- Increased strength development
- Improved shrinkage and creep behaviour
- Efficiency over a wide pH-range
- Compatible with other additives
- Low influence on hydration, thus low activator/accelerator consumption
- Free of formaldehyde and ammonia

APPROVALS / CERTIFICATES

Conforms to the requirements of EN 934-2, Table 3.1/3.2

PRODUCT INFORMATION

Composition	Modified polycarboxylate (PCE) polymer
Packaging	20 kg bag / 800 kg per pallet
Appearance / Colour	White to yellowish powder
Shelf life	24 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.
Storage conditions	Dry storage at temperatures up to 30°C. Protect from direct sunlight.
Bulk Density	0.65 ± 0.1 g/cm ³

pH-Value 4.0 ± 0.5 at +23 °C (40 % solution)

Total Chloride Ion Content ≤ 0.1 %

Equivalent Sodium Oxide ≤ 2.0 % Na₂O-equiv.)

APPLICATION INFORMATION

Recommended Dosage Depending on application the dosage rate of Sika® ViscoCrete®-125 P is between 0.05 - 0.5 % by weight of binder. At high dosage and at low temperatures Sika® ViscoCrete®-125 P can also cause retardation.

Compatibility Sika® ViscoCrete®-125 P may be combined with many other Sika products as well as with most existing accelerators, retarders and other additives used in dry-mortar applications. In these combinations with Sika® ViscoCrete®-125 P, additional improvements in flow and retardation of the mortar can also be achieved.
Important: Always conduct trials before combining products in any specific mix design and contact our Technical Services Department for any additional information and advice concerning specific combinations with other products.

Dispensing Sika® ViscoCrete®-125 P is added to the dry mix. For optimum utilisation of the high water reduction capability, a minimum wet mixing time of 30 seconds is recommended for the mortar before use.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data. Further notes and information data sheets on product safety and disposal can be found on the Internet at www.sika.de.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Deutschland GmbH
Concrete
Peter-Schuhmacher-Straße 8
69181 Leimen
Telefon: +49 06224 988-04
Telefax: +49 06224 988-522
EMail: leimen@de.sika.com



PRODUCT DATA SHEET
Sika® ViscoCrete®-125 P
July 2017, Version 01.02
02130401100000005

SikaViscoCrete-125P-en-DE-(07-2017)-1-2.pdf

