

## PRODUCT DATA SHEET

# Retardan<sup>®</sup>-2010 L

### Retarder for Calcium Sulphate Binders

#### DESCRIPTION

Retardan<sup>®</sup>-2010 L is a liquid high-performance set retarder for calcium sulphate based bound materials.

#### USES

Retardan<sup>®</sup>-2010 L provides excellent performance in the adjustment of setting time and workability of calcium sulphate based binders.

The product is especially suitable for the following application fields:

- Fabrication of gypsum boards (plasterboards / wallboards), fibreboards, partition panels, ceiling tiles & gypsum blocks
- Ready-mix production of floor screeds & self-leveling screeds based on calcium sulphate binders

#### CHARACTERISTICS / ADVANTAGES

The benefits of Retardan<sup>®</sup>-2010 L include, but are not limited to the following:

- Very efficient set retardation, already at low dosages
- Allows the setting-time adjustment of the binder slurry to the needs of the manufacturing process
- Compatible to a variety of calcium sulphate binder types and to other additives, such as Sika<sup>®</sup> ViscoCrete<sup>®</sup> superplasticizers
- Retardan<sup>®</sup>-2010 L allows the preparation of large mixes and thus reduces the application costs
- No reduction of final strength of gypsum products (unlike several fruit acids)
- Uniform quality ensures a stable manufacturing process run as well as uniformity and homogeneity of the final gypsum product
- Ecologically unproblematic, free of formaldehyde

#### PRODUCT INFORMATION

<b>Composition</b>	Aqueous solution of modified amino acid
<b>Packaging</b>	IBC of 1'000 kg net Bulk supply on demand. Smaller samples for testing are available on request.
<b>Appearance / Colour</b>	Brownish liquid
<b>Shelf life</b>	12 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.
<b>Storage conditions</b>	Storage at temperatures between 0 °C and 40 °C. Protect from direct sunlight, frost and contamination. Use clean drums/containers when delivered in bulk.
<b>Density</b>	Approx. 1.015 g/cm <sup>3</sup>
<b>pH-Value</b>	7 - 9 at +23 °C

# APPLICATION INFORMATION

## Recommended Dosage

Typical dosage range in gypsum board production: 0.03 - 0.3 % by weight of binder. Differences in calcium sulfate binder type, raw material sources, calcining methods, age and storage conditions of the binder and other individual parameters at the plant and/or job site can influence the setting time of gypsum binders and therefore the dosage of Retardan®-2010 L. Note: Preliminary testing is required to determine the exact dosage for your specific conditions. Please contact our technical service for more information and assistance.

## Compatibility

Retardan®-2010 L may be combined with many other Sika products as well as with most commonly used gypsum additives, like superplasticizer, foaming agent/ defoamer and stabilizer. In combination i.e. with Sika® ViscoCrete® superplasticizer improvements in flowability and setting-time adjustment may be achieved.

Note: Always conduct trials before combining products in specific mixes and contact our technical service for information about specific combinations with Sika® products.

## Dispensing

Retardan®-2010 L is added to the gauging water. When used in very low dosage (i.e. during gypsum board production), Retardan®-2010 L may be pre-dissolved in pure water for easier dosing. Please contact our technical service for more information and assistance.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data. Further notes and information data sheets on product safety and disposal can be found on the Internet at [www.sika.de](http://www.sika.de).

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Deutschland GmbH

Concrete  
Peter-Schuhmacher-Straße 8  
69181 Leimen  
Telefon: +49 06224 988-04  
Telefax: +49 06224 988-522  
EMail: [leimen@de.sika.com](mailto:leimen@de.sika.com)



### PRODUCT DATA SHEET

Retardan®-2010 L  
May 2019, Version 02.01  
02140601100000068

Retardan-2010L-en-DE-(05-2019)-2-1.pdf

