

## PRODUCT DATA SHEET

# SikaFiber®-12 PPF

---

**FIBRILLATED MICRO-POLYMER FIBRE FOR USE IN DRY MORTAR AND CONCRETE**

---

## DESCRIPTION

SikaFiber®-12 PPF is a special type of a synthetic micro-reinforcement. The typical application in mortar and concrete results in increased cohesion and stability in fresh concrete. Increased impact and shock resistance and reduced plastic shrinkage cracks in hardened concrete. SikaFiber®-12 PPF is not sensitive to alkalis.

## USES

- Dry mortar and dry concrete
- Screed

## PRODUCT INFORMATION

<b>Composition</b>	Polypropylene
<b>Packaging</b>	0.6 kg in biodegradable paper bags, 25 bags in cardboard box, 30 boxes on pallet
<b>Appearance and colour</b>	Fibrillated
<b>Shelf life</b>	Minimum of 2 years in sealed packaging.
<b>Storage conditions</b>	Store in dry conditions between 5° and 30°C. Protect from direct sunlight, water and dirt.
<b>Density</b>	0.91 g/cm <sup>3</sup> at +20°C
<b>Dimensions</b>	length [mm]: 12 diameter [µm]: 45 x 550
<b>Melting point</b>	165°C
<b>Ignition temperature</b>	Approx. 600°C

## CHARACTERISTICS / ADVANTAGES

- Increased resistance to shock, impact and wear stress
- Reduces cracks by plastic and/or drying shrinkage
- Higher durability
- Improvement of cohesion in the fresh concrete
- Easy to handle and dose
- Improved green strength
- No corrosion

## APPROVALS / CERTIFICATES

Complies with DIN EN 14889-2, Class Ib

## TECHNICAL INFORMATION

Resistance to alkalinity	high
--------------------------	------

## APPLICATION INFORMATION

Recommended dosage	At least 600 g per m <sup>3</sup> of fresh mortar and fresh concrete and/or 300 g per tonne of dry mortar and concrete. Approx. 900 g/m <sup>3</sup> to improve impact resistance and up to 2 kg/m <sup>3</sup> to achieve additional properties.
Compatibility	With SikaFiber®-12 PPF reinforced mortar and concrete can be pumped, installed, compacted and smoothed with common equipment and processes.
Dispensing	SikaFiber®-12 PPF is added to the dry mix in dry mortar plant, preferably with the aggregate.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Deutschland GmbH**  
Concrete  
Peter-Schuhmacher-Straße 8  
69181 Leimen  
Telefon: +49 06224 988-04  
Telefax: +49 06224 988-522  
EMail: leimen@de.sika.com



**PRODUCT DATA SHEET**  
SikaFiber®-12 PPF  
July 2022, Version 01.02  
021408021010000161

SikaFiber-12PPF-en-DE-(07-2022)-1-2.pdf

