

PRODUCT DATA SHEET

SikaBiresin® RE461 RE101

ELECTRICAL POLYURETHANE RESIN – SEMI-FLEXIBLE – SELF EXTINGUISH – UL 94 V0

APPLICATIONS

- Mechanical and numerous electrical applications for low and medium voltage when requiring an extinguish characteristic

MAIN PROPERTIES

- Semi-flexible
- Low viscosity
- Several reactivities & colors
- UL 94 V0, UL 746 HAI, HWI, RTI 150°C
- EN 45545, NF F 16101
- Good thermal conductivity & thermal resistance

DESCRIPTION

Basis	Two component polyurethane casting system		
Component A	SikaBiresin® RE461 , polyol		
	SikaBiresin® RE 461-11 -16 white	SikaBiresin® RE 461-94 black	
	SikaBiresin® RE 461-74 grey	SikaBiresin® RE 461-35 red	
Component B	SikaBiresin® RE101 , isocyanate, dark amber		

PHYSICAL PROPERTIES

			Polyol (A)	Isocyanate (B)
Component			SikaBiresin® RE461	SikaBiresin® RE101
Viscosity, 25 °C	mPa.s	ISO 2555	7,000	20
Density, 25 °C	g/cm ³	ISO 1675	1.57	1.22
Mixing ratio	by weight		100	16
Mixing ratio, 25 °C	by volume		100	20
			Mixture	
Color			White, red, grey, black	
Viscosity	mPa.s	ISO 2555	1,100	
			SikaBiresin® RE461-11	10
			SikaBiresin® RE 461-94	30
			SikaBiresin® RE 461-74- 35	35
			SikaBiresin® RE 461-16	50
Gel time, 25 °C, 200 g	min	Gel Timer TECAM		

MECHANICAL PROPERTIES

(approx. values after 16 hours / 80 °C + 24 hours / 23 °C)

Density	ISO 2781	g/cm ³	1.55
Shore hardness	ISO 868	D1 / D15	46 / 36
Tensile strength	ISO 37	MPa	7
Elongation at break	ISO 37	%	110

THERMAL AND SPECIFIC PROPERTIES

(approx. values after 16 hours / 80 °C + 24 hours / 23 °C)

Application temperature		°C	-50 / +150
Relative temperature Index RTI ³⁾	UL 746 B	°C	
Mechanical / Electrical			150/140
Glass transition temperature (T _g)	ISO 11359	°C	-5
Coefficient of thermal expansion (CTE) -40 to -20 °C / +20 to +120 °C	ISO 11359	10 ⁻⁶ K ⁻¹	45 / 140
Auto-extinguishing ³⁾	UL94		V0 6 mm ³⁾
Hot wire ignition (HWI)	UL 746 A	Category PLC	1 – 3 mm ³⁾ 0 – 6 mm ³⁾
High current arc ignition (HAI)	UL 746 A	Category PLC	0 – 3 mm ³⁾ 0 – 6 mm ³⁾
Fire behavior ¹⁾	NF F 16101	-	I 3 – F1
	EN 45545-2	R22	HL1
		R23	HL2
		R24	HL3
Water absorption (23 °C, 24 hours)	ISO 62	%	0.3
Directive 2015/863/EU (ROHS) ²⁾			Conform

¹⁾ Products SikaBiresin® RE 461-(16), SikaBiresin® RE 461-(35) and SikaBiresin® RE 461-(94) are certified EN 45545-2. SikaBiresin® RE 461-(94) is also certified NF F16101.

²⁾ European directive on the restriction of the use of certain hazardous substances electrical and electronic equipment.

³⁾ UL file number: E113398.

DIELECTRIC AND INSULATING PROPERTIES

(approx. values after 16 hours / 80 °C + 24 hours / 23 °C)

Dielectric strength (50 Hz - 1 mm)	CEI 60243-1 E2	kV/mm	25
Dielectric constant ε (100 Hz)	CEI 60250		7.7
Dissipation factor tan δ (100 Hz)	CEI 60250		0.12
Volume resistivity (1,000 V)	CEI 60093	Ω cm	2.10 ¹⁴
Tracking resistance	CEI 60112		IRC-600 - < 0.1

PACKAGING UNITS

■ Polyol (A), SikaBiresin® RE461	5 kg / 20 kg / 250 kg
■ Isocyanate (B), SikaBiresin® RE101	0.8 kg / 3.2 kg / 22 kg / 225 kg

PROCESSING DATA

- The material, processing and mold or master-model temperature shall be between 18 °C and 25 °C.
- Make sure the mold or master model is clean, dry, dust and grease free.
- Prior to use check the material for homogeneity and crystallization.
- After prolonged storage at low temperature, crystallization of components may occur. This process can be easily reversed by heating the affected component to a maximum of 70 °C until the crystals have disappeared.
- Setting may be observed on the polyol. In that case, it is necessary to mix the polyol part until both color and aspect become homogeneous. This is not harmful for the product quality.
- Both parts have to be mixed at a temperature higher than 18 °C according to the mixing ratio indicated on the technical data sheet.
- Containers must be closed tightly immediately after use to prevent moisture ingress.
- Once opened the product shall be used up as soon as possible.

STORAGE CONDITIONS

Shelf life	■ Polyol (A), SikaBiresin® RE461	12 months
	■ Isocyanate (B), SikaBiresin® RE101	12 months
Storage temperature	■ Polyol (A), SikaBiresin® RE461	15 °C – 25 °C
	■ Isocyanate (B), SikaBiresin® RE101	15 °C – 25 °C

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Advanced Resins. Copies of the following publications are available on request: Safety Data Sheets.

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and end use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Contact

SIKA DEUTSCHLAND GMBH

Business Unit Industry
Stuttgarter Straße 139
72574 Bad Urach
Phone: +49 7125 940-7692
E-Mail: industry@de.sika.com
Website: www.sika.de

SIKA AUTOMOTIVE FRANCE S.A.S.

ZI des Béthunes - 15, Rue de l'Équerre
95310 Saint-Ouen-l'Aumône
CS 40444
95005 Cergy Pontoise Cedex - FRANCE
Phone: +33 1 34 40 34 60
Fax: +33 1 34 21 97 87
E-Mail: advanced.resins@fr.sika.com
Website: www.sikaadvancedresins.fr

Sika S.A.U.

Carretera de Fuencarral, 72
28108 Alcobendas (Madrid) - SPAIN
Phone: +34 916 572 375
E-Mail: pedidos.sika@es.sika.com
Website: esp.sika.com

Sika Italia S.p.A.

Via Luigi Einaudi 6
20068 Peschiera Borromeo (MI) - Italy
Phone: +39 02 54778111
Fax +39 02 54778 119
E-Mail: info@sika.it
Website: www.sika.it

Sika Limited

Head Office, Watchmead – Welwyn
Garden City – AL7 1BQ – United Kingdom
Phone: +44 1707 394444
E-Mail: industry-sales@uk.sika.com
Website: www.gbr.sika.com

SIKA AUTOMOTIVE SLOVAKIA S.R.O.

Tovarenska 49
953 01 Zlate Moravce - SLOVAKIA
Phone: +421 2 5727 29 33
Fax: +421 37 3000 087
E-Mail: SikaAdvancedResins@sk.sika.com
Website: www.sikaadvancedresins.com

Sika Industry – Tooling, Resins and Marine

30800 Stephenson Highway
Madison Heights, Michigan 48071 - USA
Phone: +1 248 588 2270
Fax: +1 248 616 7452
E-Mail: advanced.resins@us.sika.com
Website: www.sikaindustry.com

SIKA AUTOMOTIVE EATON RAPIDS, INC.

1611 Hults Drive
Eaton Rapids, Michigan 48827 - USA
Phone: +1 517 663 81 91
Fax: +1 517 663 05 23
E-Mail: advanced.resins@us.sika.com
Website: www.sikaadvancedresins.us

SIKA MEXICANA SA de CV

Av. Gustavo Baz #309 Centrum Park
54060 Tlanepantla Estado de MEXICO
Phone: +52 442 238 5800
E-Mail: roman.octavio@mx.sika.com

SIKA AUTOMOTIVE SHANGHAI CO. LTD.

N°53 Tai Gu Road
Wai Gao Qiao
Free Trade Zone, Pudong
200131 Shanghai - CHINA
Phone: +86 21 58 68 30 37
Fax: +86 21 58 68 26 01
E-Mail: industry@cn.sika.com
Website: www.sika.cn

Sika Japan Ltd.

Akasaka-K-Tower 7F, 1-2-7, Moto-Akasaka, Minato-ku,
Tokyo · Tokyo · Tokyo · 107-0051 · Japan
Phone: +81 3-6433-2101
Fax: +81 3 6433 2102
E-Mail: advanced-resins@jp.sika.com
Website: www.jpn.sika.com

SIKA INDIA PVT LTD,

Plot No. Pap-V-90/1,
Chakan Industrial Area,
Phase-II, Vasuli, Khed, PUNE,
Maharashtra – 410501
E-Mail: info.india@in.sika.com