

PRODUCT DATA SHEET

SikaScreed®-14 L

Drying accelerator and water reducer for cement screeds tested by IBF

DESCRIPTION

SikaScreed®-14 L reduces the water demand of earth-moist to plastic consistency screed mortars which shortens the drying times for floor covering with improved processing property.

USES

SikaScreed®-14 L is particularly suitable for

- Heated screeds
- Cement screeds with high final strength
- Shortening the times to ready for covering of building site cement screeds
- Cement screeds with W/C-values of 0.50-0.42
- Bonded screeds, on separating layer or insulation
- Mechanical smoothing

FEATURES

SikaScreed®-14 L causes

- better dispersion and wetting of the cement
- Physical separation of fines
- Reduced frictional forces between cement and aggregates
- Up to 30% lower water demand

This results in cement screeds

- Strongly reduced processing and compaction effort
- Higher density and thus good thermal conductivity
- Up to 30% higher strength
- More solid surfaces
- Ready for floor covering after 7 to 14 days

CERTIFICATES AND TEST REPORTS

Examination as screed additive IBF Troisdorf. Report no. M 255/14.

PRODUCT INFORMATION

Composition	Polycarboxylate
Packaging	Canister: 10 kg; 600 kg on a pallet, Canister: 20 kg; 480 kg on a pallet; IBC of 1'000 kg net
Appearance and colour	yellowish liquid
Shelf life	12 months from date of production, if stored properly in undamaged, unopened, original sealed packaging.
Storage conditions	Protect from direct sunlight, frost and contamination. After a long storage stir before use.
Density	Approx. 1.05 g/cm ³
pH-Value	Approx. 4

APPLICATION INFORMATION

Recommended dosage

1.0 % from cement weight
approx. 0.50 l each 50 kg cement; ready for covering approx. 7 – 14 days
Formulation example CT-C25-F4 unheated, ready for covering after 2 weeks:
50 kg cement (CEM II A-LL 32,5 R)
300 kg Screed sand A/B 0-8 mm
approx. 10-13 l water (Take into account inherent moisture of the sand)
approx. 0.50 l SikaScreed® -14 L
The information refers to a 200 l screed mixing vessel and based on laboratory tests and experience. In unfavourable composed aggregates and deviating cements there may be difference strengths. After completion of the filling and closing of the mixing vessel, an additional mixing time must be maintained for 60 seconds.

Dispensing

SikaScreed®-14 L is added to the first gauging water (5-10 l) into the mixer. For optimal utilization of the liquefaction potential, we recommend a wet mixing time of 60 seconds before fine water dosage to avoid too soft consistency. The required mixing time after the addition is dependent from the mixer and must be long enough.
Before use, preliminary testing is required to determine the optimal dosage with the existing aggregates and cements. As part of this proficiency tests, the processing and technical characteristics of the screed mortar can be checked. High temperatures accelerate and low temperatures delay drying. During the drying phase adequate air exchange is to ensure.
Please contact our Technical Service Department for more information and assistance.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Deutschland CH AG & Co KG
Kornwestheimer Straße 103 - 107
D - 70439 Stuttgart
Tel.: +49 711 8009-0
Fax: +49 711 8009-321
info@de.sika.com
www.sika.de

PRODUCT DATA SHEET

SikaScreed®-14 L
August 2025, Version 01.03
021301011000001845

SikaScreed-14L-en-DE-(08-2025)-1-3.pdf