

Substrate Preparation

Substrate (for example)	Mastic asphalt screed acc. to DIN EN 13813 (AS)	Cement based screed acc. to DIN EN 13813 (CT)	Calciumsulfate- or calciumsulfate flowing screed acc. to DIN EN 13813(CA/CAF)	Dry screed
Primer (for example)	SCHÖNOX® SHP (not necessary if sufficient sanding)	SCHÖNOX® VD		
Self levelling compound (for example)	SCHÖNOX® HS 10 SCHÖNOX® HS 10 F SCHÖNOX® HS 50			SCHÖNOX® HS 10

Floor Covering Installation

Covering/ Collection	Adhesive	Tool/ trowel acc. TKB	Approx. consumption g/m ²	Remark
Designcovering (LVT)	Permanent adhesion			Range of application
Bolon sheets, tiles and acoustic tiles	SCHÖNOX® DUROCOLL Fibre reinforced, strong dispersion adhesive	TKB A1/A2	approx. 250-300 g/m ²	Pay attention to the changed residual pressure behaviour when laying on underlays!
	SCHÖNOX® PROTECT Universal adhesive for highest loads	TKB A1/A2/A4	approx. 250-370 g/m ²	
Bolon tiles and acoustic tiles	Permanent adhesion on raised floor panels			On non-absorbent substrates (e.g. raised metal floor panels) use only SCHÖNOX PROTECT!
	SCHÖNOX® DUROCOLL Fibre reinforced, strong dispersion adhesive	TKB A1/A2	approx. 250-300 g/m ²	
	SCHÖNOX® PROTECT Universal adhesive for highest loads	TKB A1/A2/A4	approx. 250-370 g/m ²	

All adhesive fulfill EC1^{PLUS} acc. to GEV requirements, unless otherwise noted.

Please follow the technical information of relevant SCHÖNOX product data sheets, the advices of the manufactures of floor covering and also according to the well-known guidelines and instructions. If in doubt please do some practical tests or call the SCHÖNOX Productservice under phone +492547/910-325. More detailed information, product data sheets or laying instructions are available under www.schoenox.com or www.bolon.com