

PRODUCT DATA SHEET

Sikaflex®-265 + SikaBooster® P-50

By Booster accelerated weathering-resistant direct-glazing adhesive and sealant

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base		Polyurethane
Color (CQP001-1)		Black
Cure mechanism		Moisture-curing ^A
Density (uncured)	Adhesive	1.2 kg/l
	SikaBooster® P-50	1.1 kg/l
Booster content	by volume	2.0 %
	by weight	1.9 %
Non-sag properties		Good
Application temperature	ambient	10 – 35 °C
Open time (CQP526-1)		20 minutes ^B
Early tensile lap-shear strength (CQP046-1 / ISO 4587)		See table 1
Shrinkage (CQP014-1)		1 %
Shore A hardness (CQP023-1 / ISO 48-4)		50
Tensile strength (CQP036-1 / ISO 527)		6 MPa
Elongation at break (CQP036-1 / ISO 527)		450 %
Tear propagation resistance (CQP045-1 / ISO 34)		14 N/mm
Tensile lap-shear strength (CQP046-1 / ISO 4587)		4.5 MPa
Service temperature (CQP513-1)		-40 – 90 °C
Shelf life	Adhesive	6 months ^C
	SikaBooster® P-50	9 months ^C
Mixer		Statomix MS 13/18 G

CQP = Corporate Quality Procedure

^{A)} provided by SikaBooster® P-50^{B)} 23 °C / 50 % r. h.^{C)} storage below 25 °C
DESCRIPTION

Sikaflex®-265 + SikaBooster® P-50 is an accelerated elastic adhesive for bonding and joint sealing in commercial-vehicle glazing applications. Its excellent weathering resistance makes it very suitable for use in exterior joints.

Sikaflex®-265 is compatible with Sika's black-primerless bonding process.

Owing to the use of SikaBooster® it cures largely independently of atmospheric conditions.

PRODUCT BENEFITS

- Fast-curing by Booster Technology
- Passes EN45545-2 R1/R7 HL3
- Suitable for bonding and sealing
- Good weathering resistance
- Solvent-free
- Low odor
- Excellent processing and tooling characteristics

AREAS OF APPLICATION

Sikaflex®-265 + SikaBooster® P-50 is designed for direct-glazing applications out of bulk packaging in the Transportation OEM market. Owing to its good tooling properties and its enhanced weathering stabilization, the product may be used for exterior joints.

The use of SikaBooster® P-50 provides rapid attainment of strength and early adhesion development.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

Sikaflex®-265 + SikaBooster® P-50
Version 04.01 (04 - 2023), en_DE
012001232650901050

CURE MECHANISM

Sikaflex®-265 + SikaBooster® P-50 cures by reaction with moisture provided by SikaBooster® P-50 and largely independent from atmospheric moisture. For typical strength build up data see table below.

Time [h]	Tensile lap-shear strength at 23 °C [MPa]
1	0.2
2	0.5
4	2.2

Table 1: Strength build-up of Sikaflex®-265 + SikaBooster® P-50

CHEMICAL RESISTANCE

Sikaflex®-265 + SikaBooster® P-50 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. All pre-treatment steps must be confirmed by preliminary tests on original substrates considering specific conditions in the assembly process.

Application

Sikaflex®-265 + SikaBooster® P-50 need to be processed with an adequate dispensing system. The mixer type needs to be respected (see table Typical Product Data).

Sikaflex®-265 + SikaBooster® P-50 can be applied between 10 °C and 35 °C but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and sealant is between 15 °C and 25 °C.

To ensure a uniform thickness of the bondline it is recommend to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

The open time is significantly shorter in hot and humid climate. The parts must always be joint within the open time. As a rule of thumb, a change of + 10 °C reduces the open time by half.

Sikaflex®-265 + SikaBooster® P-50 is processed with an adequate pump equipment. For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Tooling and finishing

Tooling and finishing must be carried out within the open time of the adhesive. We recommend the use of Sika® Tooling Agent N. Other finishing agents of lubricates must be tested for suitability and compatibility.

Removal

Uncured Sikaflex®-265 + SikaBooster® P-50 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- Sika Pre-treatment Chart
- For 1-component polyurethanes
- General Guidelines
- Bonding and Sealing with 1-component Sikaflex®

PACKAGING INFORMATION

Sikaflex®-265

Pail	23 l
Drum	195 l

SikaBooster® P-50

Unipack	600 ml
Pail	23 l

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

Sikaflex®-265 + SikaBooster® P-50
Version 04.01 (04 - 2023), en_DE
012001232650901050

Sika Deutschland GmbH

Industry
Stuttgarter Straße 139
72574 Bad Urach
Tel. +49 7125 940-7692
verkauf.industry@de.sika.com
www.sika.de

