

PRODUCT DATA SHEET

Sarnavap®-2000 E

Vapour control layer

DESCRIPTION

Sarnavap®-2000 E is an unsupported vapour control layer based on Polyethylene (PE).

USES

- Vapour control layer (VCL) is applied over most common substrates. Substrates should be smooth, dry and strong enough to support foot traffic.
- If the substrate surfaces is rough (e.g. raw concrete or sloped topping), install a levelling layer beneath Sarnavap®-2000 E.
- Sarnavap®-2000 E vapour control layer is used for Sikaplan® PVC roofs.

FEATURES

- Ease and speed of installation
- Stays flexible at low temperatures
- Non-decaying
- Constant vapour diffusion resistance

CERTIFICATES AND TEST REPORTS

- CE marking according EN 13984
- Reaction to fire according to EN 13 501-1

PRODUCT INFORMATION

Composition	Low Density Polyethylene (PE-LD) foil / High Density Polyethylene (PE-HD) foil.	
Packaging	Roll length	25.00 m
	Roll width	4.00 m
	Roll weight	23.00 kg
Appearance and colour	Surface	Smooth, PE-LD/HD foil with Sarnavap® printed on it.
	Colour	Green
Shelf life	5 years from date of production and according to defined storage conditions in unopened, undamaged, original packaging.	
Storage conditions	Rolls must be stored between +5 °C and +30 °C in a horizontal position on pallet, protected from direct sunlight, rain and snow. Do not stack pallets of rolls or any other material during transport or storage.	

Product declaration	EN 13984	
Visible defects	Pass	(EN 1850-2)
Length	25.00 m ($\pm 2\%$)	(EN 1848-2)
Width	4.00 m ($\pm 1\%$)	(EN 1848-2)
Effective thickness	0.23 mm ($\pm 10\%$)	(EN 1849-2)
Straightness	Pass	(EN 1848-2)
Max. operating pressure	230 g/m ² ($\pm 10\%$)	(EN 1849-2)

TECHNICAL INFORMATION

Resistance to impact	≤ 100 mm		(EN 12691)
Tensile strength	longitudinal	≥ 260 N/50 mm	(EN 12311-2)
	transversal	≥ 260 N/50 mm	
Elongation	longitudinal	≥ 600 %	(EN 12311-2)
	transversal	≥ 600 %	
Tear strength	longitudinal	≥ 180 N	(EN 12310-1)
	transversal	≥ 180 N	
Reaction to fire	Class E		(EN ISO 11925-2:2002) (classification to EN 13501-1)
Artificial ageing	Pass		(EN 1296 / EN 1931)
Water-vapour transmission rate	≥ 300 m		(EN 1931)
Watertightness	Pass		(EN 1928)

APPLICATION INFORMATION

Ambient air temperature	-20 °C min. / +60 °C max.
Substrate temperature	-30 °C min. / +60 °C max.

SYSTEM INFORMATION

System structure	The following products must be considered for use depending on roof design: ▪ Sarnavap® Tape F (for airtight sealing of overlaps) ▪ Sarnatape® 20 (for airtight sealing of parapets, upstands, perimeters, penetrations, flashings) ▪ Primer 130
Compatibility	Not applicable for permanent exposure to UV irradiation.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Sarnavap®-2000 E is not suitable as permanent waterproofing. It is not designed as roofing membrane and therefore can not replace the waterproofing membrane.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Substrates shall be smooth, dry and strong enough to support foot traffic.

SUBSTRATE PREPARATION

If substrate surfaces are rough (e.g. concrete or screed topping), install a levelling layer on top of substrate and underneath Sarnavap®-2000 E.

APPLICATION

1. Unroll the Sarnavap®-2000 E over the structural deck and temporarily weight in position.
2. Unroll the next roll of Sarnavap®-2000 E positioning so as to ensure a minimum 80 mm overlap.
3. Fold back the top sheet of Sarnavap®-2000 E and apply Sarnavap® Tape F (jointing tape) to the bottom sheet.
4. Peel off release tape and carefully fold back the top sheet of Sarnavap®-2000 E ensuring no wrinkles or creases are formed.
5. Apply pressure to the top sheet of Sarnavap®-2000 E with a welding roller ensuring good adhesion to the Sarnavap® Tape F. On metal decks the lap should be fully supported in order to apply the correct bonding pressure.
6. At transverse joints an airtight bond is achieved by trimming the edge of the upper sheet at 45°.
7. At perimeters and penetrations seal the Sarnavap®-2000 E by turning up and sealing to a suitable smooth surfaced abutment with Sarnatape® 20. For sealing flashing airtight, porous substrates must first be treated with Primer 130.

Sika Deutschland CH AG & Co KG
Kornwestheimer Straße 103 - 107
D - 70439 Stuttgart
Tel.: +49 711 8009-0
Fax: +49 711 8009-321
info@de.sika.com
www.sika.de

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

Sarnavap®-2000 E
July 2026, Version 02.01
020945302100000005

Sarnavap-2000E-en-DE-(07-2026)-2-1.pdf