

SikaForce[®]-7748 L10F

2 component low calorific, low cost adhesive for long production lines

Technical Product Data

Properties	Component A SikaForce [®] -7748 L10F	Component B SikaForce [®] -7010
Chemical base	Polyols, filled	Isocyanate derivatives
Color (CQP ¹ 001-1)	Beige	Brown
Color mixed	Beige	
Cure mechanism	Poly addition	
Density (CQP 006-5)	1.7 g/cm ³ approx.	1.2 g/cm ³ approx.
Density mixed (calculated)	1.6 g/cm ³ approx.	
Solid content	100 %	100 %
Mixing ratio	by volume by weight	100 : 21 100 : 15
Viscosity ² (CQP 538-2)	Brookfield - RVT 6/20 Brookfield - RVT 2/20	35'000 mPa·s approx. 250 mPa·s approx.
Viscosity (mixed)	RVT 6/20	13'000 mPa·s approx.
Application temperature	15 - 30 °C (60 - 85 °F)	
Pot life ² (CQP 536-3)	10 min. approx.	
Open time ² (CQP 590-3)	13 min. approx.	
Press time ² (CQP 590-3)	35 min. approx.	
Calorific Value (ISO 1716)	11.6 MJ/kg	
Shelf life (Storage between 10 and 30 °C)	12 months	9 months

¹ CQP = Corporate Quality Procedure

² 23 °C (73 °F)/50 % r.h.

Description

SikaForce[®]-7748 L10F is the base part of a two component polyurethane adhesive used with SikaForce[®]-7010 hardener.

Product Benefits

- Foaming
- Low calorific value

Areas of Application

SikaForce[®]-7748 L10F can be used for bonding sandwich panels for which an A2 classification, according to Constructive Product Directive, is required. This product is suitable for professional experienced users only. Test with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.



Cure Mechanism

The curing of SikaForce®-7748 L10F takes place by chemical reaction of the two components. Higher temperatures speed up and lower temperatures slow down the curing process.

Chemical Resistance

In case of chemical or thermal exposure, we recommend a project related testing. Please consult our Technical Service Department of Sika Industry for advice.

Method of Application

Surface preparation

Usually it is necessary to prepare the substrates for bonding to ensure optimal adhesion and strength. Based on the surface and type of material, a physical or chemical pre-treatment might be required after the cleaning process. Type of pre-treatment must be determined by tests.

Advice on specific applications is available from the Technical Service Department of Sika Industry.

Application

Coat weights between 150 and 350 g/m² are recommended depending on the substrates to be bonded. The specific coat weight for a given substrate combination is to be determined by tests.

Further details can be obtained from the Technical Service Department of Sika Industry.

For automated applications please contact the System Engineering Department of Sika Industry.

Pressing

An adequate bonding pressure to obtain a void-less contact between the substrates and adhesives is necessary. The specific pressure is, however, dependent on the core material and must be determined by tests. The pressure must always be below the maximum compressive strength of the core. After starting the press process do not release the pressure until the press time has elapsed.

Removal

Uncured SikaForce®-7748 L10F may be removed from tools and equipment with SikaForce®-7260 Cleaner. Once cured, the material can only be removed mechanically. Hands and exposed skin should be washed immediately using Sika® Handclean Towel or a suitable industrial hand cleaner and water. Do not use solvents!

Storage conditions

SikaForce®-7748 L10F has to be kept between 10 °C and 30 °C in a dry place. Do not expose it to direct sunlight or frost. After opening of the packaging, the content must be protected against humidity. Minimum temperature during transportation is -20 °C for max. 7 days. For B component refer to the actual Product Data Sheet.

Further Information

Copies of the following publications are available on request:

- Safety Data Sheet

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

www.sika.ch
www.sika.com

Sika Schweiz AG
Industry
Tueffenwies 16
CH-8048 Zurich
Switzerland
Tel. +41 58 436 40 40
Fax +41 58 436 55 30

