

## PRODUCT DATA SHEET

# SikaForce®-642 L4F

Foaming 2-component adhesive for panel bonding

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

Properties	Component A SikaForce®-642 L4F	Component B SikaForce®-010
Chemical base	Polyols	Isocyanate derivatives
Color (CQP001-1)	Beige	Brown
	mixed	Beige
Cure mechanism	Polyaddition	
Density (uncured)	1.56 kg/l	1.23 kg/l
	mixed (calculated)	1.48 kg/l
Solid content	100 %	100 %
Mixing ratio	by volume 100 : 32	
	by weight 100 : 25	
Viscosity (CQP029-4)	Rheometer, PP25, shear rate 10 s <sup>-1</sup> , d=1 mm	22 000 mPa·s <sup>A</sup>
	mixed	13 000 mPa·s <sup>A</sup>
Application temperature	15 – 30 °C	
Pot-life (CQP536-3)	4 minutes <sup>A</sup>	
Open time (CQP590-3)	5 minutes <sup>A</sup>	
Curing time (CQP590-3)	8 minutes <sup>A</sup>	
Gross calorific potential (EN ISO 1716)	15.6 MJ/kg	
Shelf life	6 months	9 months

CQP = Corporate Quality Procedure

A) 23 °C

**DESCRIPTION**

SikaForce®-642 L4F is a foaming 2-component polyurethane adhesive for bonding sandwich panels and similar constructions of various materials.

**PRODUCT BENEFITS**

- Can be used as a 3C system
- Low calorific value
- Solvent free
- Foaming

**AREAS OF APPLICATION**

SikaForce®-642 L4F is used for bonding sandwich panels with A2 classification according to EN14509.

The product is only suited for use on continuous production lines.

If used as 3-component system, the reactivity of the adhesive can be adapted on the production line. By changing the ratio of the adhesive mixture, individual process parameters can be met. This could be required because of line speed adjustments, or if other process parameters change. Get in contact with the Technical Department in case variable process times are required.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed, ensuring adhesion and material compatibility.

**PRODUCT DATA SHEET**

SikaForce®-642 L4F

Version 01.01 (12 - 2024), en\_DE

012104566420001030

## CURE MECHANISM

The curing of SikaForce®-642 L4F takes place by a chemical reaction of the two components. Higher temperatures speed up the curing process and lower slow it down.

## CHEMICAL RESISTANCE

In case of chemical or thermal exposure, conduct project related testing.

## METHOD OF APPLICATION

### Product preparation

Component A must be stirred thoroughly before use.

### Surface preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants. After the cleaning process, a physical or chemical pretreatment might be required, depending on surface and type of material. The type of pretreatment must be determined by tests.

During the curing process, carbon dioxide is released from the adhesive. If none of the substrates are porous, measures need to be taken to allow the carbon dioxide to escape.

### Application

Typically a coat weight between 100 g/m<sup>2</sup> and 250 g/m<sup>2</sup> is applied, depending on the substrates to be bonded. The specific coat weight for a given substrate combination must be determined by tests. For A2 classified panels, the maximum coat weight must be determined by calculation according to EN14509.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

## Pressing

An adequate bonding pressure is necessary to obtain a voidless contact between the substrates and the adhesive. The specific pressure is, however, dependent on the core material and must be determined by tests. The pressure must always be below the maximum compressive strength of the core. After starting the press process, do not release the pressure until the press time has elapsed.

## Removal

Uncured SikaForce®-642 L4F may be removed from tools and equipment with SikaForce®-096 Cleaner. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

## STORAGE CONDITIONS

SikaForce®-642 L4F has to be kept between 10 °C and 30 °C in a dry place. Do not expose it to direct sunlight or frost. After opening of the packaging, the content has to be protected against humidity.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

SikaForce®-642 L4F  
Version 01.01 (12 - 2024), en\_DE  
012104566420001030

## Sika Deutschland GmbH

Industry  
Stuttgarter Straße 139  
72574 Bad Urach  
Tel. +49 7125 940-7692  
verkauf.industry@de.sika.com  
www.sika.de

