

PRODUCT DATA SHEET

Sika® ViscoCrete®-150 P

High-Performance Superplasticizer



DESCRIPTION

Sika® ViscoCrete®-150 P is a high-performance superplasticizer and water reducer in powder form based on Sika® ViscoCrete® polycarboxylate polymer technology.

USES

Sika® ViscoCrete®-150 P is formulated for applications in cementitious and ternary binder systems. The product is suitable for the production of dry mixed mortars and concrete for applications like:

- Floor screeds, self-levelling screeds and underlayments
- Grouts, non-shrink grouts, repair mortars and tile adhesives based on Portland cement, cement blends and ternary compounds
- Dry concrete and injection mortar

CHARACTERISTICS / ADVANTAGES

Sika® ViscoCrete®-150 P, Sika's polycarboxylate technology, works based on a combination of electrostatic forces and steric repulsion effects. Thus, solid particles can be effectively dispersed.

The benefits of Sika® ViscoCrete®-150 P include, but are not limited to the following:

- High water reduction
- Excellent flowability and self-levelling behaviour
- Results in highly reduced placing- and compacting input
- Increased early strength development
- Improved shrinkage and creep behavior
- Reduced mixing times due to rapid adsorption
- Outstanding long-term stability enables long slump life
- Low influence on binder hydration
- Efficiency over a wide pH-range
- Compatible with other additives (e.g. citric acid)
- Free of formaldehyde and ammonia

APPROVALS / CERTIFICATES

Conforms to the requirements of EN 934-2, Table 3.1/3.2

PRODUCT INFORMATION

| | |
|----------------------------|--------------------------------------------------------------------------------------------------------------------|
| Composition | Modified polycarboxylates |
| Packaging | 20 kg bags /800 kg per pallet. Smaller samples for testing are available on request. |
| Appearance / Colour | White to yellowish powder |
| Shelf life | 24 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging. |
| Storage conditions | Dry storage at temperatures up to 30 °C. Protect from direct sunlight. |

PRODUCT DATA SHEET

Sika® ViscoCrete®-150 P
August 2017, Version 01.01
02130401100000043

| | |
|-----------------------------------|-------------------------------------|
| Bulk Density | 0.6 ± 0.1 g/cm ³ |
| pH-Value | 4.0 ± 0.5 at +23 °C (40 % solution) |
| Total Chloride Ion Content | ≤ 0.1 % |
| Equivalent Sodium Oxide | ≤ 2.0 % (Na ₂ O-equiv.) |

APPLICATION INFORMATION

| | |
|---------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Recommended Dosage | Depending on the application the dosage range of Sika® ViscoCrete®-150 P varies from 0.05 - 0.5 % by weight of binder. At high dosage segregation may occur as well as retardation of setting. Note: Preliminary testing is required to determine the exact dosage for your specific conditions. Please contact our technical service for more information and assistance. |
| Compatibility | Sika® ViscoCrete®-150 P may be combined with many other Sika products as well as with most existing activators/accelerators, retarders, redispersible powders, stabilizers and other additives used in dry-mix applications. In combination i.e. with other Sika® ViscoCrete® Powders and Retardan improvements in flowability and setting-time adjustment may be achieved. Note: Always conduct trials before combining products in specific mixes and contact our technical service for information about specific combinations with products. |
| Dispensing | Sika® ViscoCrete®-150 P is added to the dry mix. For optimum utilisation we recommend a minimal wet mixing time of 30 seconds for mortar. Clean all tools and application equipment with water immediately after use. |

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data. Further notes and information data sheets on product safety and disposal can be found on the Internet at www.sika.de.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Deutschland GmbH
Concrete
Peter-Schuhmacher-Straße 8
69181 Leimen
Telefon: +49 06224 988-04
Telefax: +49 06224 988-522
EMail: leimen@de.sika.com



PRODUCT DATA SHEET
Sika® ViscoCrete®-150 P
August 2017, Version 01.01
02130401100000043

SikaViscoCrete-150P-en-DE-(08-2017)-1-1.pdf

