

PRODUCT DATA SHEET

SikaDamp®-112 FE

Self adhesive sandwich of PE/PET fleece and bitumen covered with antiblocking agent

TYPICAL PRODUCT DATA

Chemical base		Polymer modified bitumen, mineral filler, iron oxide
Color (CQP001-1)	mastic layer	black
	PE/PET non-woven fleece	gray
Density	mastic layer	2.45 g/cm ³
Top layer thickness (DIN ISO 1849-1/2)	PE/PET non-woven fleece	3.8 mm
Total thickness (DIN ISO 1849-1/2)	incl. top layer	5.9 mm
Area weight (CQP008-4)	mastic layer	5 kg/m ²
	PE/PET non-woven fleece	0.3 kg/m ²
Application temperature	substrate, product	25 – 35 °C
Flammability (DIN 75200)		100 mm/min
Shelf life		4 months

CQP = Corporate Quality Procedure

DESCRIPTION

SikaDamp®-112 FE is a high-quality bitumen - PE/PET needlepunched non-woven fleece sandwich foil. It combines sound deadening and sound absorption properties on steel substrates with a very good energy saving potential for best possible energy efficiency.

The bitumen foil is filled with mineral material, iron-oxide and polymers. SikaDamp®-112 FE is equipped with a high-grade acrylic based self-adhesive system. A hot melt is applied as antiblocking agent.

The odor of SikaDamp®-112 FE is negligible in household appliances in operation up to 80 °C. At higher temperatures, a slight bitumen odor may be perceptible temporarily.

PRODUCT BENEFITS

- Sandwich-layout for energy saving and sound deadening benefits
- Sound damping
- Bitumen-sandwich foil covered with antiblocking agent
- Heat fusible
- Sound deadener
- Customized die-cut parts or sheets

AREAS OF APPLICATION

SikaDamp®-112 FE was developed for dishwashers where a combination of sound damping and energy efficient is relevant.

It can as well be used in other industrial fields where heavy-layer damping in combination with energy decoupling is required.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

SikaDamp®-112 FE

Version 01.01 (11 - 2024), en_DEAUTO

018516011120005000

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free from grease, oil, water and dust.


Application

For full-surface bonding of the self-adhesive bituminous mats, it is necessary to apply under room temperature conditions.

The recommended temperature is at least 25 °C. After removing the release paper and applying the bituminous mat to the substrate, press the mat with a roller to achieve a good wet-out of the pressure sensitive adhesive. The recommended press roll weight is approx. 2 kg.

It is necessary to ensure that all bonding surfaces are rolled in order to achieve a secure bond.

The layer structure is shown in figure 1.



1) PSA, 2) PE/PET non-woven Fleece 3) Bitumen heavy foil,
4) Hot melt as antiblocking agent

STORAGE CONDITIONS

SikaDamp®-112 FE has to be stored dry and protected from UV light. The storage temperature is between 0 °C and 35 °C. Consider, that at temperature below 15 °C the bitumen starts to get brittle and can break. Therefore, if products are sourced from a cold storage it must be handled with care.

Ensure that the product has reached the defined application temperature before it is applied. This might be realized by storing the parts for 24 to 48 hours prior application at the assembly line.

Note: Storage outside of standard conditions can affect the shelf life.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Voluntary Safety Information Sheet
- Application Manual
For SikaDamp® Applications

PACKAGING INFORMATION

Sika is delivering the finished and die-cut products on returnable steel pallets, whereas the parts are placed in the correct position for further processing. As alternative wooden one-way packaging, multiuse grid boxes and card boxes would be available.

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

This product contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet is therefore not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the Voluntary Safety Information Sheet.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.