

## PRODUCT DATA SHEET

# SikaDamp®-112 PP

Heat fusible bitumen foil with PP-foil layer

## TYPICAL PRODUCT DATA

<b>Chemical base</b>		Polymer modified bitumen, mineral filler, iron oxide
<b>Color (CQP001-1)</b>	mastic layer	Black
<b>Density</b>	mastic layer	2.4 g/cm <sup>3</sup>
<b>Top layer thickness (DIN ISO 1849-1/2)</b>		55 µm
<b>Total thickness (DIN ISO 1849-1/2)</b>	incl. top layer	2 – 4 mm
<b>Area weight (CQP008-4)</b>	depending on thickness	4.8 – 9.6 kg/m <sup>2</sup>
<b>Application temperature</b>	for 30 seconds	115 °C
<b>Loss factor (ISO 6721-3)</b>		see diagram 1
<b>Flammability (DIN 75200)</b>		100 mm/min
<b>Shelf life</b>		4 months

CQP = Corporate Quality Procedure

**DESCRIPTION**

SikaDamp®-112 PP is a standard heavy layer, flexible bitumen foil for sound deadening and sound damping applications on steel substrate.

The bitumen heavy foil is filled with mineral material, iron oxide and polymers. SikaDamp®-112 PP is covered with a PP-foil and equipped with a polyamid hot melt adhesive.

The odor of SikaDamp®-112 PP is negligible in household appliances in operation up to 80 °C. At higher temperatures, a slight bitumen odor may be perceptible temporarily.

**PRODUCT BENEFITS**

- Sound deadener
- Sound damping
- Bitumen heavy foil covered with PP-foil
- Heat fusible
- Customized die-cut parts or sheets

**AREAS OF APPLICATION**

SikaDamp®-112 PP was initially developed for the noise damping in the field of household appliances, such as dishwashers (steel tub), washing machine, tumble dryer and small appliances. It can as well be used in other industrial fields, where damping with high density bitumen foils is required.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

**PRODUCT DATA SHEET**

SikaDamp®-112 PP

Version 04.03 (07 - 2023), en\_DEAUTO

018516011120013000

## METHOD OF APPLICATION

### Surface preparation

Surfaces must be clean, dry and free from grease, oil, water and dust.

### Application

During application, the hot melt adhesive must reach 115 °C for a period of at least 30 seconds.

It is common practice in the industry to heat the bitumen material from the bitumen side in order to soften the bitumen material first and to achieve a full surface contact of the mat before the hot melt adhesive is activated. For information regarding typical loss factors, see diagram 1. The layer structure is shown in figure 1.




Diagram 1: Loss factor SikaDamp®-112 PP at 200 Hz




Figure 1: 1) PP-foil, 2) Bitumen based PSA, 3) Bitumen heavy foil, 4) Hot melt

## STORAGE CONDITIONS

SikaDamp®-112 PP has to be stored dry and protected from UV light. The storage temperature is between 0 °C and 35 °C. Consider, that at temperature below 15 °C the bitumen starts to get brittle and can break. Therefore, if products are sourced from a cold storage it must be handled with care.

Ensure that the product has reached the defined application temperature before it is applied. This might be realized by storing the parts for 24 to 48 hours prior application at the assembly line.

Note: Storage outside of standard conditions can affect the shelf life.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Voluntary Safety Information Sheet

## PACKAGING INFORMATION

Sika is delivering the finished and die-cut products on returnable steel pallets, whereas the parts are placed in the correct position for further processing.

As alternative wooden one-way packaging, multiuse grid boxes and card boxes would be available.

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

This product contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet is therefore not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the Voluntary Safety Information Sheet.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.