

## PRODUCT DATA SHEET

# SikaScreed<sup>®</sup>-02 L

Compactability aid for earth-moist cement screeds

### DESCRIPTION

SikaScreed<sup>®</sup>-02 L increases the compactability of earth-moist to plastic consistency screed mortars and results in higher strength by introduction of air pores at the same time.

### USES

SikaScreed<sup>®</sup>-02 L is particularly suitable for:

- Increase of compactability
- Cement screeds with W/C-values of 0.50-0.60
- Bonded screeds, on separating layer or insulation
- Screed mortar for vibration tile method
- Cement screeds with high final strength
- Screeds for in- and outdoor

### CHARACTERISTICS / ADVANTAGES

SikaScreed<sup>®</sup>-02 L causes

- better dispersion and wetting of the cement
- Reduced frictional forces between cement and aggregates
- introduction of fine, evenly distributed air pores
- lower water demand

This results in cement screeds

- better workability at the same water-cement-ratio
- reduce W/C-value with the same workability properties
- Higher strength
- Higher frost thaw resistance
- Lower shrinkage
- Even and compact surface

### PRODUCT INFORMATION

Composition	Ligno sulfonate
Packaging	Canister: 10 kg; 600 kg on a pallet; Canister: 20 kg; 480 kg on a pallet;
Appearance / Colour	brown liquid
Shelf life	12 months from date of production, if stored properly in undamaged, unopened, original sealed packaging.
Storage conditions	Protect from direct sunlight, frost and contamination. After a long storage stir before use.
Density	Approx. 1.11 g/cm <sup>3</sup> (+20°C)
pH-Value	Approx. 5

## APPLICATION INFORMATION

<b>Recommended Dosage</b>	<p>0.2-0.6 % from cement weight; approx. 0.30 l each 50 kg cement</p> <p><u>Formulation example CT-C25-F4:</u> 50 kg cement (CEM II A-LL 32,5 R) 300 kg Screed sand A/B 0-8 mm approx. 12-15 l water (Take into account inherent moisture of the sand) approx. 0.30 l SikaScreed® -02 L</p> <p>The information refers to a 200 l screed mixing vessel and based on laboratory tests and experience. In unfavourable composed aggregates and deviating cements there may be difference strengths. After completion of the filling and closing of the mixing vessel, an additional mixing time must be maintained for 90 seconds.</p>
<b>Compatibility</b>	<p>Before use, preliminary testing is required to determine the optimal dosage with the existing aggregates and cements. As part of this proficiency tests, the processing and technical characteristics of the screed mortar can be checked. High temperatures accelerate and low temperatures delay drying. During the drying phase adequate air exchange is to ensure.</p> <p>Please contact our Technical Service Department for more information and assistance.</p>
<b>Dispensing</b>	<p>SikaScreed®-02 L is added to the first gauging water (5-10 l) into the mixer. For optimal utilization of the liquefaction potential, we recommend a wet mixing time of 60 seconds before fine water dosage to avoid too soft consistency. The required mixing time after the addition is dependent from the mixer and must be long enough.</p>

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Deutschland GmbH**  
Concrete  
Peter-Schuhmacher-Straße 8  
69181 Leimen  
Telefon: +49 06224 988-04  
Telefax: +49 06224 988-522  
EMail: leimen@de.sika.com



**PRODUCT DATA SHEET**  
SikaScreed®-02 L  
April 2020, Version 01.02  
021404061000000113

SikaScreed-02L-en-DE-(04-2020)-1-2.pdf