

PRODUCT DATA SHEET

SikaBiresin® F27 F55

Unfilled fastcast resin for rotomolding production

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Component A SikaBiresin® F27	Component B SikaBiresin® F55
Chemical base	Polyol, unfilled	MDI-based isocyanate, unfilled
Color	Beige	Colorless
	mixed	White
Density	1.02 kg/l	1.22 kg/l
	cured	1.1 kg/l
Mixing ratio	by weight 100 : 80	
Viscosity (CQP029-4)	70 mPa·s	250 mPa·s
	mixed	140 mPa·s
Pot life (CQP021-4)	200 g at 23 °C 1 minute 30 seconds	
Demolding time	15 minutes	
Curing time	at 23 °C 3 days	
Shore D hardness (CQP023-1 / ISO 868)	75 ^A	
Tensile strength (CQP036-2 / ISO 527)	40 MPa ^A	
Elongation at break (CQP036-2 / ISO 527)	7 % ^A	
Flexural strength (CQP027-2 / ISO 178)	60 MPa ^A	
Flexural modulus (CQP027-2 / ISO 178)	1500 MPa ^A	
Impact resistance (CQP038-2 / ISO 179)	50 kJ/m ² ^A	
Heat deflection temperature (CQP030-1 / ISO 75B)	75 °C ^A	
Shelf life	12 months	

CQP = Corporate Quality Procedure

^A) curing condition: after demolding 7 days at 23 °C

DESCRIPTION

SikaBiresin® F27 F55 is an unfilled fast curing 2-component polyurethane system suitable for rotomolding production of hollow molds.

PRODUCT BENEFITS

- High quality of surface detail reproduction
- Low shrinkage and good dimensional stability
- Short pot life and demolding time
- Can be easily machined
- Very fine structure

AREAS OF APPLICATION

SikaBiresin® F27 F55 is designed for casting of master and core models, negatives and moldings of small up to medium dimensions.

The Product is suitable for applications across thin layers.

SikaBiresin® F27 F55 is well suited for casting of art and crafts articles. Due to the low viscosity it can reproduce very fine surface details.

Due to its short pot life and demolding time, the Product can be used for rotomolding production of hollow molds.

This product is suitable for experienced professional users only.

PRODUCT DATA SHEET

SikaBiresin® F27 F55

Version 01.01 (07 - 2026), en_DE

012122020270901000

METHOD OF APPLICATION

Surface preparation

The material, processing and mold or master-model temperature shall be between 18 °C and 25 °C.

Make sure the mold or master model is clean, dry, dust and grease free.

If mold or master-model surface is porous, it must be sealed prior applying the release agent.

It is recommended to use wax-based release agents. For further information regarding Sika release agent consult the corresponding Product Data Sheet.

Mixing process

Prior to use check the material for homogeneity and crystallization. After prolonged storage at low temperature, crystallization of components may occur. This process can be easily reversed by heating the affected component to a maximum of 70 °C until the crystals have disappeared. Allow to cool down to requested processing temperature before use.

Consider, pot life is affected by temperature and mixed quantity.

Prior to mixing, component A must be shaken thoroughly. To shake large containers, place them on a table and then carefully turn them over and move them back and forth.

If no fillers are needed, pour both components in the right mixing ratio together and mix homogeneously.

In case fillers are required, divide the filling quantity evenly and mix homogeneously into each of the two components respecting the defined mixing ratio. The mixing can be performed with a spatula or a machine stirrer at ≤ 300 rpm.

Then pour both components together and mix homogeneously. In both cases, to ensure homogeneous and complete mixing, pour the mixed product into another container and mix again shortly, considering the pot life.

Note: Both containers must be closed tightly immediately after use to prevent moisture ingress.

Once opened the product shall be used as soon as possible.

Application

Immediately after mixing pour the Product into the mold starting at the deepest point.

Demolding time may vary depending on casted thickness and room temperature.

STORAGE CONDITIONS

Both components must be stored at temperature between 15 °C and 25 °C in original unopened containers.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

PACKAGING INFORMATION

SikaBiresin® F27 (A)

Canister	5 kg 20 kg
Drum	200 kg

SikaBiresin® F55 (B)

Canister	5 kg 20 kg
----------	---------------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

SikaBiresin® F27 F55
Version 01.01 (07 - 2026), en_DE
012122020270901000

Sika Deutschland CH AG & Co KG

Industry
Stuttgarter Straße 139
72574 Bad Urach
Tel. +49 7125 940-7692
verkauf.industry@de.sika.com
www.sika.de

