

PRODUKTDATENBLATT

SikaMelt[®]-880

Reaktiver Polyolefin hot melt für Montage Anwendungen

TYPISCHE PRODUKTEIGENSCHAFTEN (WEITERE ANGABEN SIEHE SICHERHEITSDATENBLATT)

Chemische Basis	Polyolefin
Farbe (CQP001-1)	Weiss – beige
Härtungsmechanismus	Feuchtigkeitshärtend
Dichte	0,9 kg/l
Viskosität (Brookfield)	bei 180 °C 8 000 mPa·s
Erweichungspunkt (CQP538-5)	159 °C
Applikationstemperatur	160 – 200 °C
Durchhärtungszeit (CQP558-1)	20 h
Anfangsfestigkeit (CQP557-1)	0.8 MPa
Zugfestigkeit (CQP036-3)	2.0 MPa
Haltbarkeit	9 months

CQP = Corporate Quality Procedure

BESCHREIBUNG

SikaMelt[®]-880 is a reactive hot melt adhesive based on polyolefin technology which cures on exposure to atmospheric humidity to a durable elastomer. It shows a good adhesion performance on polypropylene with high durability.

PRODUKTVORTEILE

- Very good adhesion to polypropylene substrates without pre-treatment
- Short open time
- High green strength
- High final strength and flexibility over a broad temperature range
- Good ageing and heat resistance

ANWENDUNGSBEREICH

SikaMelt[®]-880 is especially designed for assembly applications of polypropylene materials. It is also suitable to bond on wood, textiles, non-woven materials and foams. Depending on the application polar plastics (ABS, PC and PA) can be joined as well. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

HÄRTUNGSMECHANISMUS

SikaMelt®-880 cures by reaction with atmospheric moisture. At low temperatures the water content in the air is lower, which will result in a lower curing speed (see diagram 1). When bonding hydrophobic (e.g. PP) and/or moisture impermeable substrates a significantly longer curing time has to be taken into account. This applies especially on assembly applications with an adhesive thickness > 100 µm. For lamination applications of hydrophobic and/or moisture impermeable substrates the adhesive layer shall not exceed 100 µm. In such cases project related tests with original substrates and conditions are mandatory.




Diagram 1: Curing time for 500 µm film

CHEMISCHE BESTÄNDIGKEIT

SikaMelt®-880 is resistant to aqueous surfactant, weak alkaline/acids solutions and temporarily resistant to fuels, solvents and mineral oils.

The chemical resistance is influenced by several factors such as chemical composition, concentration, period of exposure and temperature. Therefore a project related testing in case of chemical or thermal exposure is required.

VERARBEITUNGSHINWEISE

Oberflächenvorbereitung

Surfaces must be clean, dry and free from grease, oil and dust.

Verarbeitung

With adequate processing equipment SikaMelt®-880 can be applied as film, dot, bead or spray application.

For automated applications a suitable filter system is required.

To meet the required application properties the adhesive viscosity can be adjusted by adapting the application temperature (see table Typical Product Data).

During breaks SikaMelt®-880 is to be processed as follows:

For breaks ≥ 1 h the heating needs to be lowered to 80 °C and for breaks ≥ 4 h the heating needs to be switched off.

To guarantee a constant quality during the whole production process it is mandatory to protect the adhesive in the melting tank with nitrogen, carbon dioxide or dried air (to avoid possible reaction of the product with humidity). At breaks or shut downs dip nozzle in dried oil in order to prevent humidity to cure the adhesive (avoid blockage).

For advice on selecting and setting up suitable processing equipment contact the System Engineering Department of Sika Industry.

Entfernung

Equipment and application tools can be cleaned with SikaMelt®-005 (see also Cleaning Instructions).

SikaMelt®-880 may be removed from tools and equipment with Sika® Remover-208 or another suitable solvent.

Hands and exposed skin have to be washed immediately using Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

LAGERBEDINGUNGEN

SikaMelt®-880 has to be stored at temperature below 40 °C in a dry place.

For transportation purposes, the storage temperature can be exceeded for a period of max. 2 weeks up to 60 °C.

WEITERE INFORMATIONEN

Copies of the following publications are available on request:

- Safety Data Sheets
 - Manual Cleaning Instructions
- For SikaMelt®-88x (Reactive APAO hot melts)

VERPACKUNG

Bag	1.5 kg
Pail	15 kg
Drum	140 kg

BASIS DER TECHNISCHEN DATEN

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ARBEITSSCHUTZBESTIMMUNGEN

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

RECHTLICHER HINWEIS

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.