

PRODUCT DATA SHEET

SikaTard®-810 P

Retarder for cementitious and ternary systems in powder form



DESCRIPTION

SikaTard®-810 P is an economical set retarder in powder form for cementitious and CAC-based ternary dry mortar systems.

USES

SikaTard®-810 P delivers exceptional results when adjusting the setting and processing time of accelerated and unaccelerated dry mortars and concrete. In some mortar systems, the consistency is improved and the flow behavior is supported.

The product is especially suitable for the following applications:

- Dry concrete with long open times
- Non-shrink grouts
- Self-levelling underlayments (SLU) CAC-based
- Repair mortars
- Flowable cementitious screeds
- Masonry mortar

PRODUCT INFORMATION

| | |
|-----------------------------------|--|
| Composition | Mix of organic and inorganic components |
| Packaging | 25 kg bag, 1050 kg per pallet; bigbag on demand |
| Appearance / Colour | light gray powder |
| Shelf life | 24 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging. |
| Storage conditions | Dry storage at temperatures up to 40 °C. Protect from direct sunlight. |
| Bulk density | Approx. 1.28 g/cm ³ |
| pH-Value | Approx. 11.5 (40 % solution) |
| Total chloride ion content | ≤ 0.1% |
| Equivalent sodium oxide | < 3.5 % |

CHARACTERISTICS / ADVANTAGES

SikaTard®-810 P retards the cement reaction with water.

The benefits of SikaTard®-810 P include, but are not limited to the following:

- Good retarding effect depending on dosage
- Relatively low effect on strength development
- Slightly positive influence on consistency
- Combinations with other retarders possible e.g. tartaric acid
- Easy to dose with automatic dosage equipment
- Excellent stability in dry mortar formulations

APPROVALS / CERTIFICATES

Confirms to the requirements of EN 934–2, Table 8 (retarder)

APPLICATION INFORMATION

| | |
|---------------------------|--|
| Recommended dosage | Typical dosage range: 0.2 - 0.9 % of binder weight. Differences in cement type, cement age and storage conditions of the binder and other conditions and factors at the plant and/or on-site can also influence the setting time and therefore the dosage requirements. Note: Preliminary testing is required to determine the exact dosage for specific applications and conditions. Please contact our Technical Services Department for any additional information and assistance. |
| Compatibility | SikaTard®-810 P may be combined with most existing redispersible powders, accelerators, retarders and other additives used in dry-mix applications. Important: Always conduct trials before combining products in specific mix designs and contact our Technical Service Department for any additional information and advice concerning specific combinations with other products. |
| Dispensing | SikaTard®-810 P is added to the dry mix. |

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data. Further notes and information data sheets on product safety and disposal can be found on the Internet at www.sika.de.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Deutschland GmbH
Concrete
Peter-Schuhmacher-Straße 8
69181 Leimen
Telefon: +49 06224 988-04
Telefax: +49 06224 988-522
EMail: leimen@de.sika.com



PRODUCT DATA SHEET
SikaTard®-810 P
March 2021, Version 01.01
021406011000000166

SikaTard-810P-en-DE-(03-2021)-1-1.pdf

