

PRODUCT DATA SHEET

SikaBiresin® L90

Laminating paste for reinforcement of big negatives, models and molds

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	SikaBiresin® L90 (A)	SikaBiresin® L90 (B)
Chemical base	Epoxy resin	Amine
Color	Grey	Blue
	mixed	Light blue
Mixing ratio	by weight	100 : 14
Density		
	1.0 kg/l	0.96 kg/l
	cured	1.0 kg/l
Viscosity (CQP538-2 / BROOKFIELD LVT)	Pasty	140 mPa·s
	mixed	Pasty
Pot life (CQP021-3 / Gel Timer TECAM)	500 g at 23 °C	60 minutes
Demolding time		24 hours
Maximal laminating thickness		25 mm
Shore D hardness (CQP023-1 / ISO 868)		73 ^A
Flexural modulus (CQP027-2 / ISO 178)		3800 MPa ^A
Compressive strength (CQP028-5 / ISO 604)		50 MPa ^A
Heat deflection temperature (CQP030-1 / ISO 75B)		60 °C ^A
Shelf life		12 months

CQP = Corporate Quality Procedure

^{A)} curing condition: 23 °C for 7 days

DESCRIPTION

SikaBiresin® L90 is a smooth laminating paste for reinforcement of big negatives, models, molds and tools.

PRODUCT BENEFITS

- Easy mixing with colored hardener component for mixing control
- Very smooth with good adhesion
- Up to 25 mm thickness in one operation
- Mixtures are emulsifiable with water under uncured conditions
- Curing without strain and with low heat build-up
- Cured laminates can be machined

AREAS OF APPLICATION

SikaBiresin® L90 is suitable for the reinforcement of big negatives, models, molds and tools.

It enables the construction of complex and demanding reinforcement layers.

The Product is designed for the production of dimensionally accurate laminates and reinforcement layers with high precision.

It is also well suited for lightweight laminate constructions requiring high dimensional stability and accuracy.

This product is suitable for experienced professional users only.

METHOD OF APPLICATION

Surface preparation

The material and processing temperature shall be between 18 °C and 25 °C.

Mixing process

Component B must be shaken well before use.

Both components must be mixed homogeneously respecting the defined mixing ratio.

The required mixing quality is achieved when the mixture has a uniform color.

Small amounts of 1 – 2 kg can be processed by hand, for greater amounts it is recommended to use mechanical mixer with dough hook.

Prolonged mixing may raise the temperature of the reaction mass and shorten the pot life. Containers must be closed tightly immediately after use to prevent moisture ingress.

Once opened the Product shall be used as soon as possible.

Application

If larger quantities are prepared it is recommended to divide the mass in smaller portions to avoid a faster exothermic reaction.

It is recommended to use a coupling layer and apply the ready-mixed laminating paste in an even layer.

Apply small patches to avoid air entrapment.

Smooth and compact the layers with a roller or by hand.

Depending on laminate thickness and processing temperature, the demolding time and the pot life of the laminating resin may vary.

STORAGE CONDITIONS

Both components must be stored at temperature between 15 °C and 25 °C in original unopened containers.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

PACKAGING INFORMATION

SikaBiresin® L90 (A)

Hobbock	15 kg
---------	-------

SikaBiresin® L90 (B)

Canister	2.1 kg
----------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

SikaBiresin® L90
Version 01.01 (09 - 2026), en_DE
013122040900001000

Sika Deutschland CH AG & Co KG

Industry
Stuttgarter Straße 139
72574 Bad Urach
Tel. +49 7125 940-7692
verkauf.industry@de.sika.com
www.sika.de

