

PRODUCT DATA SHEET

SikaShield® EP 5 PLUS ard WF flam

Elastomeric bitumen membrane with polyester fleece inlay as torch applied root resistant roofing capping sheet

DESCRIPTION

SikaShield® EP 5 PLUS ard WF flam (thickness 5.2 mm) is a root resistant elastomeric bitumen membrane reinforced with a polyester fleece.

The top side is granulated with slate and the bottom side is laminated with a polyethylene torch-foil. The top side longitudinal overlap area has an onesided PET-foil edge strip.

USES

Roofing and waterproofing membrane

- Green roof as cap layer

FEATURES

- Elastic behaviour at low temperatures
- Robust, tear-resistant and stretchable reinforcement
- Root resistant and ecologically harmless
- High break down strength
- High hail resistance
- UV-resistant
- High resistance to weathering
- Chemically good compatible

CERTIFICATES AND TEST REPORTS

- CE-Marking and declaration of performance according to EN 13707 - Bitumen sheets for roof waterproofing -national implementation- DIN/TS 20.000-201:2025-02
- Classification Report from external fire exposure – Institute for Material Testing, University of Stuttgart
- Resistance to root penetration – Institute of Horticulture, University of Applied Sciences Weihenstephan-Triesdorf

PRODUCT INFORMATION

Composition	coating reinforcement	elastomeric bitumen roof retardant polyester fleece $\geq 230 \text{ g/m}^2$
Packaging	single rolls	
Appearance and colour	top bottom	slate granule, foil-laminated edge trim foil-laminated
Shelf life	24 months if stored properly	
Storage conditions	Store vertical and protected from extreme external influence as such heat, cold, moisture etc.	
Visible defects	free of visible defects	(EN 1850-1)

Length	5 m	(EN 1848-1)
Width	1 m	(EN 1848-1)
Thickness	5.2 mm [+10% / -5%]	(EN 1849-1)
Straightness	< 20 mm / 10 m	(EN 1848-1)
Mass per unit area	5.6 kg/m ² [± 10%]	(EN 1849-1)

TECHNICAL INFORMATION

Resistance to impact	≥ 2.000 mm	(EN 12691 - A+B)
Resistance to static loading	≥ 20 kg	(EN 12730 - A+B)
Resistance to root penetration	passed	(EN 13948, FLL - procedure)
Tensile strength	maximum tensile force	(EN 12311-1)
	lengthwise	≥ 900 N / 50 mm
	crosswise	≥ 800 N / 50 mm
Elongation	elongation at maximum tensile force	(EN 12311-1)
	lengthwise	≥ 35 %
	crosswise	≥ 35 %
Dimensional stability	≤ 0.4 %	(EN 1107-1)
Tear strength	nail shank	(EN 12310-1)
	lengthwise	≥ 250 N
	crosswise	≥ 250 N
Joint shear resistance	shear resistance	(EN 12317-1)
	lengthwise	≥ 700 N / 50 mm
	crosswise	≥ 700 N / 50 mm
External fire performance	B _{roof} (t1) * * according to systeme testing	(EN 13501-5)
Reaction to fire	class E	(EN 13501-1, EN ISO 11295-2)
Water-vapour transmission rate	s _d = 400 m [± 20%]	(EN 1931 - procedure A)
Watertightness	400 kPa	(EN 1928 - procedure B)
Flow resistance	+120 °C	(EN 1110)
Flexibility at low temperature	-25 °C	(EN 1109)

APPLICATION INFORMATION

Ambient air temperature	We recommend a minimum temperature of +5 °C during the application.
Substrate temperature	We recommend a minimum temperature of +5 °C during the application.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Bitumen membranes coated with slate granules are natural products; weather and environmental conditions may cause changes in the surface, color, or appearance, for which the manufacturer assumes no liability.

To achieve the most uniform appearance possible,

contiguous areas should be installed using material from the same production batch.

ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding or torching) in closed rooms.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

General provisions on substrate quality:

The substrate must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, oil, dust and loosely adhering particles.

Substrate preparation:

Use the appropriate preparation equipment to achieve the required substrate quality.

General provisions for the application:

Strictly follow installation procedures as defined in method statement, application manuals and working instructions which must always be adjusted to the actual site conditions.

All corresponding processing standards and regulations must be obeyed.

Protection:

The membrane must be protected from damage during any ongoing site activities.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Deutschland CH AG & Co KG

Kornwestheimer Straße 103 - 107

D - 70439 Stuttgart

Tel.: +49 711 8009-0

Fax: +49 711 8009-321

info@de.sika.com

www.sika.de

PRODUCT DATA SHEET

SikaShield® EP 5 PLUS ard WF flam

June 2026, Version 03.01

020920011990001952

SikaShieldEP5PLUSardWFFlam-en-DE-(06-2026)-3-1.pdf